

H750I Warehouse Markers Data Sheet

Subject	Result	Test Method
Material	PVC laminated with DST	N/A
Type of adhesive	Solvent acrylic (0.1mm)	N/A
PVC	0.3mm rigid film	Caliper method
DST	0.084mm	N/A
Total applied thickness	0.384mm	Caliper method
Peel adhesion to stainless steel, 20 minute dwell. N/25mm	18.9	FINAT FTMI
Peel adhesion to stainless steel, 24 hour dwell. N/25mm	25.7	FINAT FTMI
Resistance to water (months)	10	PSTC-35
Resistance to chemicals (months)	8	PSTC-35
Resistance to motor oil	Excellent	PSTC-35
Temperature range	-30°C ~ +70°C	See notes below

The independent test laboratory at Adhesive Technical Services Ltd performed the temperature test, England (test results available)

	Test Result	Test Method
Coefficient of Friction Category	R10	DIN51130

All the above data is for reference only.

©Heskins Ltd 1997-2024